

+ **Plasticolors® GTS Colorants**

Colorants and tinting system solutions for Gel Coats

Plasticolors® GTS colorants for gel coat applications contain highly durable organic and inorganic pigments dispersed in a monomer free, unsaturated polyester carrier resin. The GTS colorants are developed as a tinting system for volumetric and gravimetric use in dispensing machines. The system provides greater color flexibility and ensures efficient and accurate production of a large variety of colored gel coats.

► **Application**

Chromaflo Technologies GTS colorants have been specifically developed for gel coat applications. The colorants demonstrate excellent compatibility with commonly used gel coat systems (for example Ortho, ISO, ISO-NPG) for both brush and spray applications.

► **Properties**

A list of the GTS colorants is included on the reverse of this page. On request other colorants can be added to the system to support individual needs. The GTS colorants are suitable for pumping and metering in automated systems and are calibrated by volume and weight. The colorants have very little or no impact on the performance and properties of the gel coats. With a limited amount of colorants the GTS system offers a great choice of color shades like RAL colors or any other required customized shades or color collections. The colorants consist of high performance pigments to enhance durability.

► **Packaging and storage**

The GTS colorants are available in a variety of packaging. Please contact Chromaflo Technologies for more information.

Containers should be tightly sealed when not in use. This will prevent the absorption of atmospheric moisture and minimize the chance of airborne contamination.

Containers should be stored in a manner as to protect them from temperature extremes (0-45°C). Material should be mixed prior to use. The Best Before Use Date is 24 months from the date of manufacture.

► **Our services**

Chromaflo Technologies Europe supplies pigment pastes and chemical dispersions in Europe, North Africa and the Middle East. Manufacturing and technical support is provided from our Maastricht site in the Netherlands.

Our technical professionals are available to support you with your inhibitor, thickening and color requirements.

Our dedicated sales managers are your point of contact for any queries you have. Apart from direct contact with our sales managers, we have set up a broad network of distribution partners to enhance local support. A large palette of standard colors, custom color matched blends and toll manufacturing can be offered.

Contact us to learn more about our chemical dispersions and pigment pastes for your application. Information on the product portfolio in other regions can be provided on request.



Product code	Description	CI Name	Pigment content of colorant [%]	Light Fastness of Pigment ¹		Weather Resistance of Pigment ²		Density of Colorant (kg/m ³)
				Mass	Tint	Mass	Tint	
GTS-10762	White	White 6	55	8	N/A	5	N/A	1.76
GTS-02823	Black	Black 7	12	8	8	5	5	1.24
GTS-30653	Phthalo Blue	Blue 15:3	17	8	8	5	4-5	1.10
GTS-30735	Cobalt Blue	Blue 28	50	8	8	5	5	1.78
GTS-50292	Phthalo Green	Green 7	15	8	8	5	5	1.18
GTS-50334	Green Oxide	Green 17	58	8	8	5	5	2.13
GTS-60269	Organic Orange	Orange 36	25	8	7-8	5	4-5	1.20
GTS-60297	Organic Orange	Orange 73	18	8	8	5	4-5	1.03
GTS-70950	Magenta	Red 122	9	7-8	7-8	4-5	4-5	1.09
GTS-70951	Red Oxide	Red 101	57	8	8	5	5	1.90
GTS-70952	Organic Red	Red 254	22	7-8	7-8	4-5	4	1.18
GTS-070078	Violet	Violet 23	13	8	8	5	4	1.08
GTS-80825	Yellow Oxide	Yellow 42	42	8	8	5	5	1.74
GTS-80823	Bismuth Yellow	Yellow 184/154	35	8/8	8/8	4-5/5	5/5	1.38

The values given in the table are guidance figures only. The data is obtained from pigment suppliers, individual testing is recommended.

¹ Light fastness is measured on an eight step blue scale, where 1 = very poor light fastness, 8 = excellent light fastness.

² Weather resistance is measured on a five step gray scale, where 1 = very poor weather resistance, 5 = excellent weather resistance.

©Chromaflo Technologies. This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.