

+ Colortrend® 870 Low-VOC*

In-plant Colorants

Used to tint latex, emulsion and water-based paints, Colortrend® 870 In-Plant Colorants are Low-VOC. They are very high strength colorants utilizing the same pigments as Colortrend® 888 Universal Colorants and Colortrend® 808 Low-VOC Colorants.

Therefore, color matching between plant and retail store is extremely accurate and non-metameric. Colortrend® 870 Colorants are quality controlled for consistent performance at any depth of shade. Tint strength is controlled, in a Tint Base, to +/- 2% with a maximum CIELAB DE of 0.50 units.

► **Color Systems**

Colortrend® 870 Colorants are higher strength, in-plant coloristically equivalent versions of the Colortrend® 888 and Colortrend® 808 Low-VOC System Colorants. These colorants are suitable for use in many custom-designed color systems and color offerings. Starting point formulations for various types of latex and solvent-based paints for these systems are available.



Product Code	Description	Typical Lbs/Gal	Specific Gravity	% Composition by Weight			% Composition by Volume			VOC	
				Pigment Solids	Vehicle	Volatiles	Pigment Solids	Vehicle	Volatiles	Lbs /Gal	g/L
870-0018	Titanium White	17.2	2.07	66.9	18.9	14.2	33.6	37.0	29.4	0	0
870-0422	Magenta	9.8	1.18	38.4	16.8	44.8	29.1	18.2	52.7	0	0
870-0445	Magenta	9.7	1.16	39.6	17.4	43.1	31.6	18.5	49.9	0	0
870-0825	Hp Red	11.7	1.40	46.3	21.4	32.3	25.7	29.0	45.3	0	0
870-0832	Organic Red	10.3	1.24	44.2	20.3	35.5	23.1	33.0	43.9	0	0
870-1045	Red Oxide	17.4	2.09	33.1	18.1	48.8	17.6	23.6	58.8	0	0
870-1572	Brown Oxide	14.7	1.16	60.0	27.0	13.0	48.2	24.7	27.1	0	0
870-1811	Yellow Oxide	15.3	1.84	55.0	28.0	17.0	43.9	24.8	31.3	0	0
870-2022	Raw Umber	14.2	1.70	54.5	19.6	25.9	27.5	28.4	44.1	0	0
870-2042	Medium Yellow	10.3	1.24	57.2	13.9	28.9	14.5	49.8	35.7	0	0
870-2092	Raw Umber	13.1	1.56	49.4	23.9	26.8	24.1	34.1	41.8	0	0
870-2522	Organic Yellow	10.8	1.30	57.1	15.2	27.7	15.3	48.8	35.9	0	00
870-5522	Phthalo Green	11.4	1.37	47.2	16.2	36.6	35.2	14.6	50.2	0	0
870-7222	Phthalo Blue	10.1	1.21	41.1	23.0	35.9	27.2	29.3	43.5	0	0
870-9907	Black	10.8	1.30	33.6	34.5	31.9	40.5	18.0	41.5	0	0
870-9914	Med. Strength Black	12.0	1.44	48.1	14.6	37.3	17.9	28.3	53.8	0	0
870-9922	High Strength Black	10.8	1.30	45.9	14.7	39.4	15.8	33.1	51.1	0	0

**Per ASTM D6886-12, per EPA Method 24 Calculation all of 0 g/L

©ChromaFlo Technologies. This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.



Where Art Meets Technology