

Colortrend® 878

+ In-Plant Colorants

COLORTREND® 878 in-plant colorants for latex, emulsion and water-based paints produce thousands of colors using only 12 colorants. In addition, the ethylene glycol-free system is based on the same pigments as those used in COLORTREND® universal machine dispensable colorants. The use of the same pigments eliminate metamerism, allowing for good matches between in-plant and store tinted paints.



► Permanence & High Solar Exposure

When formulating with COLORTREND® 878 dispersions, consideration must be given to special circumstances of use and their effect on colorant durability. Examples of such conditions are tropical or subtropical climates, deserts and ocean-fronting locations. In each of these instances the solar radiation received is significantly greater than most other environments. The use of organic pigments in these situations should be considered only after careful evaluation of the fastness of the colorant/ vehicle combination to ensure it will meet the expected performance. For positive verification of lightfastness and durability, we recommend that the colorants be tested under accelerated or actual weathering conditions in the coating system and on the substrates where they will be employed.

► Compatibility

COLORTREND® 878 in-plant colorants are compatible with all types of water-borne systems such as:

- PVA emulsions
- Styrene-butadiene emulsions
- Acrylic emulsions
- Other water-based systems

► Other Applications

COLORTREND® 878 in-plant colorants can be used in many types of emulsion products requiring coloring. For example:

- Aqueous graining inks
- Wax emulsions for lumber marking
- Leather and floor polish
- Latex adhesives
- Coated papers
- Christmas tree coloring
- Grass paints
- Emulsion fabric coatings
- Leather coatings
- Rubber latex compounds
- Aqueous plastic and foams
- Artist paint

Product Code	Description	Typical Lbs/Gal	Specific Gravity	% Composition by Weight			% Composition by Volume			VOC	
				Pigment Solids	Vehicle Solids	Volatiles	Pigment Solids	Vehicle Solids	Volatiles	Lbs/Gal	g/L*
878-0019	Titanium White	16.8	2.03	67.6	8.8	23.6	35.5	17.7	46.9	2.1	246
878-0423	Magenta	9.1	1.28	18.2	12.1	69.7	13.4	12.9	73.7	3.9	468
878-0837	Organic Red	9.7	2.30	25.6	11.0	63.4	19.4	12.0	68.5	3.5	420
878-1046	Red Oxide	18.0	1.12	62.6	9.4	28.0	25.0	19.0	56.0	2.2	259
878-1573	Brown Oxide	15.6	1.12	59.1	7.8	33.1	24.4	14.4	61.2	2.3	279
878-1812	Yellow Oxide	16.5	1.35	62.7	8.6	28.7	30.1	16.2	53.7	1.8	210
878-2010	Raw Umber	12.7	1.16	46.4	8.3	45.3	21.8	12.2	66.0	2.7	324
878-2041	Medium Yellow	10.0	1.22	41.2	11.5	47.3	32.8	13.3	53.8	3.5	414
878-2552	Organic Yellow	10.3	1.98	45.8	11.1	43.1	37.6	12.9	49.5	1.8	210
878-5512	Phthalo Green	11.0	2.07	25.6	25.2	49.2	13.6	29.4	57.0	2.3	271
878-7215	Phthalo Blue	9.2	1.72	17.9	18.6	63.5	12.1	20.0	67.9	2.2	268
878-8895	Carbazole Violet	9.0	1.70	8.0	32.8	59.2	5.2	33.9	60.9	1.6	189
878-9908	Lamp Black	10.9	1.75	46.0	9.3	44.8	32.4	11.7	55.9	2.3	270

©Chromaflo Technologies. This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.



Where Art Meets Technology