

Colortrend® 877

+ In-Plant Colorants

COLORTREND® 877 color dispersions are high-strength, pourable color pastes recommended for in-plant tinting of emulsion and water-based paints. All colorants have a 6 minimum fineness of grind (Hegman gauge) which makes COLORTREND® 877 dispersions exceptionally suitable for the tinting of latex paints. They can also be used for the economical formulation of deep accent paints, thus avoiding the grinding of dry pigment. COLORTREND® 877 dispersions contain a broad color spectrum, selected to satisfy all the tinting needs of the manufacturer and contractor.



► High Solar Exposure

When formulating with COLORTREND® 877 colorants, consideration must be given to special circumstances of use and their effect on colorant durability. Examples of such conditions are: tropical or subtropical climates, deserts and ocean-fronting locations. In each of these instances the solar radiation received is significantly greater than most environments. The use of organic pigments in these situations should be considered only after careful evaluation of the fastness of the colorant/ vehicle combination to ensure it will meet the expected performance. The most reliable method of testing is to expose the coating under the expected conditions of use.

► Other Uses

COLORTREND® 877 dispersions can be used in many types of emulsion products requiring coloring. For example: aqueous graining inks, wax emulsions for lumber marking, leather and floor polish, latex adhesives, coated papers, Christmas tree coloring, grass paints, emulsion fabric coatings, leather coatings, rubber latex compounds, aqueous plastics and foams, and artists' paints.

► Permanence

The pigments used in COLORTREND® 877 colorants were selected to provide a wide range of hues, good durability, lightfastness, and alkali resistance. However, the lightfastness, alkali resistance, and weathering properties of pigments (particularly organic reds and yellows) depend a great deal on the coatings, substrate and application conditions. For positive verification of lightfastness and durability, we recommend that the colorants be tested under accelerated or actual weathering conditions in the coating system and on the substrates where they will be employed.

► Chemistry and Compatibility

COLORTREND® 877 dispersions are compatible with all types of latices such as:

- Styrene Butadine
- Semi-Gloss and Gloss Latices
- Polyvinyl Acetate
- Alkyd Resin Emulsions
- Acrylics
- Water Type Coatings
- Vinyl Acetate – Ethylene Copolymers
- Alkyd Modified Latices

Product Code	Description	CI Number	Typical Lbs/Gal	Specific Gravity	% Composition by Weight			% Composition by Volume			VOC	
					Pigment Solids	Vehicle Solids	Volatiles	Pigment Solids	Vehicle Solids	Volatiles	Lbs/Gal	g/L*
878-0019	Titanium White	PW 6	16.9	2.03	67.6	8.8	23.6	35.5	17.7	46.9	2.1	246
877-0451	Quinacridone Red	PV 19	10.7	1.28	39.4	15.1	45.5	24.2	19.0	56.8	2.0	245
877-0548	Indian Red	PR 101	19.2	2.30	68.4	10.5	21.2	29.8	23.4	46.8	2.1	250
877-0578	Organic Red	PR 112	10.2	1.22	49.4	7.7	42.9	42.6	5.6	51.8	2.8	330
877-0726	Toluidine Red b/s	PR 3	9.3	1.12	21.5	10.6	67.9	16.1	11.4	72.5	3.5	425
877-0787	Fast Red	PR123	11.0	1.35	33.1	18.1	48.8	17.6	23.6	58.8	4.9	584
877-0801	Naphthol Red	PR 112	9.6	1.16	40.0	0.7	59.3	31.8	0.8	67.5	1.5	182
877-0925	Dinitro Orange	PO 5	10.3	1.22	45.0	8.2	46.8	36.4	9.6	54.0	2.1	249
877-1035	Red Oxide	PR 101	17.1	2.07	62.5	10.0	27.5	24.6	20.2	55.2	2.1	252
877-1107	Burnt Sienna	PBr 7	14.7	1.72	57.2	9.0	33.9	24.8	15.8	59.4	2.1	254
877-1314	Burnt Umber	PBr 7	14.3	1.70	56.0	10.4	33.6	29.2	16.8	54.0	1.8	218
877-1403	Light Raw Umber	PBr 7	14.9	1.75	56.9	9.1	34.0	30.0	15.1	54.9	2.3	274
877-1573	Brown Oxide	Blend	15.6	1.86	59.1	7.8	33.1	24.4	14.4	61.2	2.3	279
877-1703	Tan	Blend	14.7	1.72	56.8	9.8	33.4	26.7	16.9	56.4	2.1	254
877-1811	Yellow Oxide	PY 42	14.8	1.81	56.5	8.5	35.1	25.5	14.8	59.7	2.6	307
877-1812	Yellow Oxide	PY 42	16.4	1.98	62.7	8.6	28.7	30.1	16.2	53.7	1.8	210
877-2010	Raw Umber	PBr 7	13.4	1.64	55.3	12.1	32.7	28.3	19.4	52.3	1.7	198
877-2020	L/F Medium Yellow	Blend	10.3	1.24	41.2	11.3	47.6	33.5	13.3	53.2	3.6	437

©Chromaflo Technologies. This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.



Where Art Meets Technology

Product Code	Description	CI Number	Typical Lbs/Gal	Specific Gravity	% Composition by Weight			% Composition by Volume			VOC	
					Pigment Solids	Vehicle Solids	Volatiles	Pigment Solids	Vehicle Solids	Volatiles	Lbs/Gal	g/L*
877-2066	Medium Azo Yellow	Blend	9.6	1.16	34.6	6.7	58.7	25.2	7.8	67.1	1.9	224
877-2501	Med. Perma-Cal Yellow	Blend	10.6	1.27	43.8	11.8	44.4	36.0	13.7	50.3	1.9	226
877-2505	Hi Tint Azo Yellow	PY 74	9.5	1.13	28.0	8.9	63.1	20.4	10.0	69.7	1.9	225
877-2528	Hansa Yellow	PY74	11.3	1.37	48.3	10.9	40.8	28.2	25.8	46.0	2.3	270
877-2530	L/F Light Yellow	PY 74	11.9	1.42	46.2	11.4	42.4	31.0	15.5	53.5	4.2	501
877-2553	Hi-Strength Yellow	PY 74	10.2	1.20	51.4	7.9	40.7	41.2	9.6	49.2	1.7	201
877-2554	Hi-Strength Yellow	PY74	9.5	1.25	36.7	5.6	57.7	29.2	6.2	64.6	1.0	118
877-2823	Hansa Yellow 10G	PY 3	11.3	1.37	49.7	7.2	43.1	34.6	9.4	55.9	2.2	261
877-4206	Chromium Oxide	PG 17	17.0	2.04	64.0	7.1	28.9	25.6	14.8	59.6	2.7	329
877-5513	Phthalo Green	PG 7	11.2	1.32	42.5	7.6	49.9	25.3	9.9	64.8	2.2	258
877-7027	Phthalo Blue G/S	PB 15:3	9.6	1.13	24.4	10.2	65.5	16.9	11.2	72.0	1.6	194
877-7034	Phthalo Blue I/S	PB 15:2	9.7	1.16	39.3	7.0	53.8	28.5	8.3	63.2	1.9	228
877-7227	Phthalo Blue	PB 15:2	9.4	1.09	43.1	15.8	41.1	32.0	19.7	48.3	0.8	101
877-7505	Ultramarine Blue	PB 29	13.1	1.56	60.0	8.6	31.4	39.0	13.2	47.8	2.0	241
877-8895	Carbazole Violet	PV 23	11.0	1.30	33.0	18.4	48.6	16.8	24.1	59.1	4.4	531
877-9908	Lamp Black	PBk 7	10.9	1.30	46.0	9.3	44.8	32.4	11.7	55.9	2.3	270
877-9910	Hi-Strength Black	PBk 7	10.8	1.30	45.0	8.6	46.5	32.0	10.9	57.2	2.6	308
877-9918	Tinting Black	PBk 7	10.8	1.30	45.0	8.9	46.1	31.6	11.2	57.3	2.3	281
877-9921	Econo Black	PBk 7	10.6	1.27	44.1	4.0	52.0	30.5	4.9	64.6	2.2	269
877-9940	Stain Black	PBk 7	10.1	1.21	31.7	11.7	56.6	27.3	8.5	64.2	2.7	325
877-9998	Carbon Black	PBk 7	10.5	1.27	40.0	7.0	53.1	27.3	8.5	64.2	2.7	325

©Chromaflo Technologies. This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.



Where Art Meets Technology